

Technical Information

OPTAL A 08 FR 15



Type of adhesive water base synthetic adhesive

Field of application **Labelling** : pick up adhesive
Other applications : bonding paper, paper on aluminium foil

Product specifications

Test Method

Viscosity 30 000 - 50 000 mPa.s Brookfield RVT 7/20/20

pH-value 5.5 - 7.5

Solid content 16 - 19 %

Product properties

Film OPTAL A 08 FR 15 has a good wet tack and is very easy to clean with hot water

Processing

Application Segment, roll
Most suitable processing temperature : 18 - 25° C.
OPTAL A 08 FR 15 can't be blended with other adhesives like starch, dextrin, or casein adhesives.

Cleaning Uncured adhesive residues can easily be removed with water

Disposal see Safety Data Sheet

Protective Measures see Safety Data Sheet

Storage Conditions/Shelf Life

In closed original packaging 12 months from date of production.
Optimum storage temperature: 10 - 35 °C, protect from frost.
Close containers thoroughly after use.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention. GC/JL June 2003

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050
Email: info@van-asperen.nl www.van-asperen.nl

www.industrial-adhesives.com



Technologies
Industrial Adhesives