Technical Information Purmelt CB 2007-21



I. Product Description

Adhesive TypePurmelt CB 2007-21 is a moisture curing reactive Polyurethane hotmelt with a high initial tack and a good transparenz.

Application areas Purmelt CB 2007-21 is especially suitable for the production on folding cartons and

clear boxes. All plastic films as A-PET, G-PET, pretreated Polyolefin and PVC films can be used. All materials have to be well pretreated (> 38dyn) and tested before

in industrial trials.

Product Properties Purmelt CB 2007-21 is fast setting and shows a very high initial tack after cooling.

After curing with moisture the highly transparent adhesive film has a duroplastic character leading to a high temperature stability and high flexibility even at low

temperatures.

Typical Characteristics

Solids 100%

Viscosity 8000 +-2000mPas, Brookf. RVT, Sp. 27, 30 rpm, 130 °C Colour clear to slight yello, transparent when melted and after cooling

II. Instructions for Use

Processing

Premelting unit: 100-130 ℃ Hose: 120-150 ℃ Nozzle: 140-160 ℃

Depending on the application unit and the machine the parameters has to be

individually adjust for a good wetting and optic.

If the machine is stopped for extended periods, the temperature should be reduced

in the melting unit and in the hoses to avoid increase in viscosity.

Curing Depending on humidity, thickness of adhesive layer and film quality, the adhesive

Status: 02/2008

will achieve final bond strength after 2-5 days. For curing an ambient temperature of at least 20 °C has to be assured. Lower temperatures will slow down curing. After physical setting the adhesive has already a high handling strength. To obtain a bubble free adhesive seam the adhesive bean should be pressed to form a thin

and even adhesive film.

Cleaning For the cleaning of application equipment we recommend our product

Purmelt Cleaner 2.

Disposal See material safety datasheet

Safety information See material safety datasheet.

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad

Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050 Email: info@van-asperen.nl Website: www.van-asperen.nl



Purmelt CB 2007-21

III. Transport / Storage

ClassificationPlease refer to the safety data

sheet.

Storage In closed original packaging 9 months at 5-25 ℃.

The containers should be stored in a dry environment. The adhesive should be

used directly after opening the container.

The Information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes ad applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Status: 02/2008

Düsseldorf, February 2008

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050

Email: info@van-asperen.nl Website: www.van-asperen.nl

