

# Technical Information

## Adhesin A 2225

van Asperen  
KLEEFSTOFFEN

<b>Type of adhesive</b>	synthetic resin dispersion, containing plasticizer	
<b>Field of application</b>	Low viscous and fast setting adhesive for the packaging industry for unlacquered materials. General bonding of paper	
<b>Product specifications</b>		<b>Test method</b>
<b>Viscosity</b>	900 ± 200 mPa.s	Brookfield RVDV 2/20/23, ISO 2555
<b>pH-value</b>	4,5 ± 1,0	ISO 976
<b>Product properties</b>	Adhesin A 2225 forms an elastic film.	
<b>Processing</b>		
<b>Application</b>	by means of electromagnetic valves most suitable working temperature is 18 – 25 °C	
<b>Dilution</b>	Adhesin A 2225 can be diluted with cold water if required.	
<b>Cleaning</b>	Uncured adhesive residues can easily be removed with water. Wetting agents accelerate the cleaning process.	
<b>Disposal</b>	See Safety Data Sheet	
<b>Protective Measures</b>	See Safety Data Sheet	
<b>Storage conditions/ Shelf Life</b>	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 – 25 °C, protect from frost. Stir the adhesive before use. Close packaging thoroughly after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.  
Düsseldorf, September 2002

