

Technical Information

Adhesin A 2305

van Asperen
KLEEFSTOFFEN

Type of adhesive	emulsion-based adhesive on basis of synthetic resin containing plasticizer	
Field of application	Packaging industry bonding of unlacquered papers and cardboards on common packaging machines; closing- and folding box machines; folder gluers Bags and pouches manufacturing side seam glueing of all kinds of unlacquered papers; carrier bags manufacturing Laminating imitation chromo board with E-flute	
Product specifications		Test method
Viscosity	4.500 ± 1.500 mPa.s	Brookfield RVT 4/20/23, ISO 2555
pH-value	4,5 ± 1,0	ISO 976
Product properties	Adhesin A 2305 is a very fast setting adhesive for bonding of unlacquered papers, glassine- and imitation parchment papers, painted- and strong calendered papers. The adhesive shows a good fluidity.	
Film	soft elastic	
Processing Application	by means of roller, disc, nozzle	
Temperature	optimum working temperature: 18 - 25 °C	
Dilution	Adhesin A 2305 is ready for use, but can be diluted with cold water if required.	
Cleaning	Uncured adhesive residues can easily be removed with water. Wetting agents accelerate the cleaning process.	
Disposal	see Safety Data Sheet	
Security advices	see Safety Data Sheet	
Shelf life	6 months in closed original packaging	
Storage conditions	Optimum storage temperature: 15 - 25 °C, protect from frost. After use close packaging thoroughly.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, August 2000

