

# Technical Information

## Adhesin A 2306

**van Asperen**  
KLEEFSTOFFEN

<b>Type of adhesive</b>	emulsion-based adhesive on basis of synthetic resin containing plasticizer	
<b>Field of application</b>	Packaging Industry bonding of unlacquered papers and cartons on common packaging machines; closing- and folding box machines; folder gluers	
<b>Product specifications</b>		<b>Test method</b>
<b>Viscosity</b>	10.000 $\pm$ 2.000 mPa.s	Brookfield RVT 5/20/23, ISO 2555
<b>pH-value</b>	4,5 $\pm$ 1,0	ISO 976
<b>Product properties</b>	Adhesin A 2306 is a concentrated adhesive with a high setting speed and good flowing properties.	
<b>Film</b>	soft elastic	
<b>Processing Application</b>	by means of roller, disc, segment	
<b>Temperature</b>	optimum working temperature: 18 - 25 °C	
<b>Dilution</b>	Adhesin A 2306 is ready for use, but can be diluted with cold water if required.	
<b>Cleaning</b>	Uncured adhesive residues can easily be removed with water. Wetting agents accelerate the cleaning process.	
<b>Disposal</b>	see Safety Data Sheet	
<b>Security advices</b>	see Safety Data Sheet	
<b>Shelf life</b>	6 months in closed original packaging	
<b>Storage conditions</b>	Optimum storage temperature: 15 - 25 °C, protect from frost. After use close packaging thoroughly.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Düsseldorf, February 1995

