

ENVATEX 292
072-0292

0499/MB/03

Description

Formulated rubber latex adhesive.
(ammonia stabilised)

Appearance

Cream liquid.

Technical Characteristics

Viscosity (Brookfield
Sp. 3, 20 rpm)

Typical Data

1,300 mPa.s. @ 23°C

Solids (105C for 1 hour)

59%

pH

10.2

Specific Gravity (100ml SG cup)

0.95

Typical Applications

* Envelope self-seal.

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted and no statement made herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers before using any product make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions. Such as evaluation should be repeated if materials are changed in any way or bought from a different source. No agent or representative of our has any authority to vary, omit or otherwise alter these terms.

Application Guide

Apply by roller applicator or multi-stencil gummer. Not suitable for use with brass equipment.

Suggested coating weight 12 - 15 gsm dry (wallets), 15-20 gsm (pockets).

Finished envelopes should be stored vertically in sealed containers. The ability to self-seal will deteriorate with time, particularly under the influence of heat, light and surface contamination.

Packaging

Consult local sales office.

Storage & Handling

Rotate stock using oldest material first.

Keep covered to prevent contamination and drying out.

Do not mix with other adhesives.

Store at 7-30°C and out of sunlight.

Shelf life : For best results use within 2 months from day of delivery.

HEALTH & SAFETY

Users should familiarise themselves with the safety data sheet before using or handling this product.

The information given and the recommendations made herein are based on our experience and are believed to be accurate. No guarantee as to, or responsibility for, their accuracy can be given or accepted and no statement made herein is to be treated as a representation or warranty. In every case we urge and recommend that purchasers before using any product make their own tests to determine, to their own satisfaction, its suitability for their particular purposes under their own operating conditions. Such as evaluation should be repeated if materials are changed in any way or bought from a different source. No agent or representative of our has any authority to vary, omit or otherwise alter these terms.