

Adhesin A 3231 VL

March-2010

PRODUCT DESCRIPTION

Adhesin A 3231 VL provides the following product characteristics:

Technology	Synthetic Resin Dispersion
Product Type	Dispersion containing plasticizer
Application	Bookbinding Industry

Application Areas

Perfect binding on binding machines with or without drying station.

Film Properties

- elastic
- transparent

Technical Data

Adhesin A 3231 VL:

Viscosity, Brookfield - RVT, 6/20/23, mPa.s	9,000 to 15,000
ISO 2555	
pH value	3 to 5
ISO 976	

DIRECTIONS OF USE

Preliminary Statement

Prior to application it is necessary to read the Safety Data Sheet for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labeling, the relevant precautions should always be observed. Please also refer to the local safety instructions and contact Henkel for analytical support.

Application

Application method:

- roller

Most suitable processing temperature: 18 - 25 °C.

Dilution

Adhesin A 3231 VL can be diluted with cold water if required.

Cleaning

Uncured adhesive residues can easily be removed with water. Wetting agents accelerate the cleaning process.

Handling Information

Due to the variety of different materials available on the markets pre-tests should be carried out.

STORAGE

Protect from freezing.

Close containers thoroughly after use.

Shelf life:

Shelf-life (in unopened original packaging), 6 months

Frost-Sensitive Yes

Recommended Storage Temperature, °C 15 to 25

Classification:

Please refer to the corresponding safety data sheets for details on:

Hazardous Information

Transport Regulations

Safety Regulations

ADDITIONAL INFORMATION

Disclaimer:

The Information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention. This datasheet replaces all former versions.

Reference 0.0