



4945F Acrylic Foam Tape

Product Data Sheet

Updated : March 1996
Supersedes : October 1993

Product Description

VHB Joining Systems utilise firm acrylic adhesives which have excellent long term holding power. The peel adhesion and tensile holding power

of products in the VHB family are significantly higher than typical pressure sensitive tape products. Resistance to solvents, temperature extremes, and

U.V. light make VHB products suitable for many interior and exterior applications.

Physical Properties

Not for specification purposes

Adhesive Type	Acrylic	3M ref : A-30
Thickness (ASTM D-3652) Tape Liner Total	1.10 mm 0.05 mm 1.15 mm	
Foam Density	800 kg/m ³	
Adhesive Carrier	Acrylic Foam (Closed Cell)	
Release Liner	Red Film	
Tape Colour	White	
Shelf Life	24 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics

Not for specification purposes

Peel Adhesion to Stainless Steel 90° peel @ room temp, 72 hr dwell, jaw speed 300mm/min	44 N/10mm	
Static Shear Strength weight held for 10,000 mins to stainless steel with ½ sq in (3.23 sq cm) overlap	1500 g @ 20°C 500 g @ 66°C 500 g @ 93°C	
Normal Tensile (T-Block) to Aluminium at room temp, 6.45 sq cm, jaw speed 50 mm/min	97 N/cm ²	

Date : March 1996
4945F Acrylic Foam Tape

Performance Characteristics (Cont...) Not for specification purposes	Temperature Performance (Minutes/Hours) (Days/Weeks)	150 °C 93 °C	
	Solvent Resistance <small>Splash testing cycle - 20 seconds submersion - 3 cycles.</small>	No apparent degradation when exposed to splash testing of most solvents including gasoline, JP-4 jet fuel, mineral spirits, motor oil, ammonia cleaner, acetone, methyl ethyl ketone. 20 seconds air dry.	
	UV Light Resistance	Excellent.	

Additional Product Information	<p>Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact and thus improves bond strength.</p> <p>To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol/water mixture (rubbing alcohol) or heptane. Use proper safety precautions for handling solvents.</p>	<p>It may be necessary to seal or prime some substrates prior to bonding.</p> <p>a. Most porous or fibred materials (e.g. wood) will require sealing to provide a unified surface.</p> <p>b. Some materials (e.g. copper, brass, plasticised vinyl) will require priming or coating to prevent interaction between adhesive and substrates.</p>	<p>Ideal tape application temperature range is 20 to 38°C. Initial tape application to surfaces at temperatures below 15°C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.</p> <p>In some cases bond strength can be increased and ultimate bond strength can be achieved more quickly by exposure of the bond to elevated temperatures (e.g. 65°C for one hour). This provides better adhesive wetout on to the substrates.</p>
---------------------------------------	---	---	---

Applications	<p>VHB Joining Systems are suited for use in many interior and exterior industrial applications. In many situations, they can replace rivets, spot welds, liquid adhesives and other permanent fasteners. Each product in the VHB family has specific strengths. These can include high tensile, shear and peel adhesion and resistance to solvents, moisture and plasticiser migration. All VHB tapes should be thoroughly evaluated by the</p>	<p>user under actual use conditions with intended substrates, especially if expected use involves extreme environmental conditions.</p> <p>VHB Joining Systems are suitable for bonding a variety of substrates, including sealed wood, many plastics, composites and metals. Plastics which can be a problem are polyethylene, polypropylene, teflon, silicones and other low surface energy materials.</p>	<p>Galvanised surfaces are potential problems and should be carefully evaluated.</p> <p>To prevent corrosion on copper and brass, only lacquer coated material should be used within VHB Joining Systems.</p> <p>Thorough evaluations are recommended when bonding is required to any questionable surface.</p>
---------------------	--	--	--

Date : March 1996
 4945F Acrylic Foam Tape

Special Feature Products	4945F has very good plasticiser resistance and adhesion to vinyl. Because of the wide variation in vinyl formulation, however, evaluation must be conducted with the specific vinyl used to insure that performance is satisfactory. Problems related to plasticiser migration can often be predicted by accelerated ageing at 65°C for one week.	<u>4945F Feature</u>	Adhesion to plasticised materials.
		Acrylic Foam Tape 4945F utilises an acrylic adhesive which provides excellent adhesion to many paint finishes and plasticised vinyls.	Plasticisers are common ingredients in many soft, flexible plastics. These plasticisers can migrate into adhesives causing a reduction in bond strength. Adhesive bond performance is dependent on the types and concentrations of plasticisers used in the plastic formulation. Acrylic Foam Tape 4945F is resistant to migration of many plasticisers and should be evaluated for applications requiring bonding to flexible plastics.
		Adhesion to painted surfaces.	
		There is a wide variety of paint systems available and specific recommendations cannot be made. For painted surface, Acrylic Foam Tape 4945F should be evaluated along with other VHB Tape products.	

Underwriters Laboratories (U.L.) Recognition

U.L. 746-C Temperature Rating

Substrate	Temperature (°C)
Unplasticised (Nylon 6-6)	75
ABS and Polycarbonate	90
Polyamide (Nylon 6-6)	90
Galvanised Steel and Aluminium	110
Enamelled Steel and Phenolic	110

3M and VHB are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes.
 Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.
 This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M is a trademark of 3M Company.



3M Nederland BV Industriële Tapes & lijmen Postbus 193 2300 AD Leiden	e-mail: 3mbonding.nl@mmm.com internet: www.3m.nl/tapes www.3m.nl/lijmen	Customer Service: Tel.: (071)5 450 187 Fax: (071)5 450 376
--	--	--