



# 904 (ATG Version) Transfer Tape

## Product Data Sheet

Updated : June 2000  
Supersedes : February 1996

**Product Description** General purpose clear acrylic adhesive Transfer Tape on white polycoated paper liner, with good temperature performance.

**Physical Properties**  
Not for specification purposes

<b>Adhesive Type</b>	Acrylic	<b>3M ref :</b>
<b>Thickness</b> (ASTM D-3652) Tape Liner Total	0.05 mm 0.10 mm 0.15 mm	
<b>Release Liner</b>	White Polycoated Silicone Paper	
<b>Tape Colour</b>	Clear	
<b>Shelf Life</b>	12 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50% Relative Humidity.	

**Performance Characteristics**  
Not for specification purposes

<b>Adhesion to Stainless Steel</b> ASTM D-3330	904 adheres well to most high energy surfaces and plastic materials (ABS, PP, etc). Well suited for bonding a wide variety of similar or dissimilar materials.
<b>Solvent Resistance</b>	Relative high solvent resistance
<b>Temperature Resistance</b>	Relative high temperature operating range. Continuous exposure: 120°C. Short term: 200°C. (up to 240°C for minutes).
<b>UV Light Resistance</b>	Excellent UV resistance
<b>Peel Adhesion (AFERA 4001)</b>	5 N/10 mm.

Date : June 2000  
904 (ATG Version)  
Transfer Tape

- 
- Application Techniques**
1. Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure develops better adhesive contact & thus improves bond strength.
  2. To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Typical surface cleaning solvents are isopropyl alcohol and water (rubbing alcohol) or heptane. Use proper safety precautions for handling solvent.
  3. ATG System is the cleaner, easier, more precise way to lay down a strip of 904 adhesive transfer tape.
  4. Ideal tape application temperature range is 20°C to 40°C. Initial tape application to surfaces at temperatures below 10°C is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.
- 

**Applications**

Web splicing (paper, foil, film, fabrics).

Core starting.

Miscellaneous joining and holding where high initial adhesion and long ageing bond is required.

Foams, pictures, posters, etc. laminations.

3M is a trademark of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications. This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



**Tapes & Adhesives**

© 3M United Kingdom PLC 1996

3M United Kingdom PLC  
3M House,  
28 Great Jackson Street,  
Manchester,  
M15 4PA

Product Information :  
Tel 0870 60 800 50  
Fax 0870 60 700 99

3M Ireland  
3M House, Adelphi Centre,  
Upper Georges Street,  
Dun Laoghaire, Co. Dublin,  
Ireland

Customer Service :  
Tel (01) 280 3555  
Fax (01) 280 3509