



Scotch-Weld™

EPX™ Epoxy Adhesive DP460

Product Data Sheet

Updated : March 1996
Supersedes : January 1995

Product Description	DP460 epoxy adhesive is a room temperature curing, two part epoxy adhesive supplied in 3M Duo-Pak cartridge for use with the 3M EPX Applicator.	DP460 offers the following features: High shear strength. High Peel strength.	2:1 premix strength allowing gap filling. Outstanding environmental resistance. Easy mixing and controlled flow.
----------------------------	---	--	--

Physical Properties

Not for specification purposes

	BASE	ACCELERATOR
Base	Modified Epoxy	Modified Amine
Viscosity (cP at 23°C)	80,000	10,000
Specific Gravity	1.12	1.08
Colour	White	Amber
Work Life	60 minutes at 23°C.	
Handling Strength	240 - 360 minutes at 23°C	
Full Strength	5 days (test to full performance at one week)	
Standard 3M Shelf Life	24 months from date of despatch by 3M when stored in the original carton at 21°C (70°F) & 50 % Relative Humidity	

Performance Characteristics

Not for specification purposes

T-Peel Strength	Measured on abraded, steel (0.8mm) at 24°C. 43.9 N/cm (25 piw).	
	Measured on Etched Aluminium at 23°C (60 piw).	

Date : March 1996
EPX Epoxy Adhesive DP460

Performance Characteristics (Cont...)
Not for specification purposes

Overlap Shear Strength

The following strength values were obtained with DP460 when tested after 7 day cure cycle at 24°C.

Substrates solvent wiped, abraded and solvent wiped prior to bonding.

	MPa	psi
Galvanised Steel	13.8	2000
Cold Rolled Steel	19.3	2800
FPL Etched Aluminium	31.0	4500
Copper	27.6	4000
Stainless Steel	27.6	4000
Brass	27.6	4000
Acrylic	2.3	330
PVC	2.4	350
Polycarbonate	3.4	500
Neoprene/Steel	0.8*	120*
SBR/Steel	1.0*	140*
ABS	4.0	575
FRP	6.9*	1000*

* Denotes Substrate Failure

Environmental Resistance Etched Aluminium. Overlap shear tested at 23°C.

Environment	Condition	Etched AL (MPa)	Galv Steel (MPa)
23°C / 50% RH	30 days	35.8	15.2
Distilled Water	30 days immersion	35.2	15.9
Water Vapour	50°C / 100% RH, 30 days 93°C / 100% RH, 14 days	34.5 21.4	13.1 10.3
Antifreeze/H ₂ O (50/50)	82°C 30 day immersion	34.5	13.8
Isopropanol	23°C 30 day immersion	39.3	13.8
Methyl Ethyl Ketone	23°C 30 day immersion	29.0	13.8
Salt Spray 5%	65°C 30 days	35.2	13.1

Electrical Properties

Dielectric Strength (Volts/mm)	2.8 x 10 ⁴	
Volume Resistivity (Ohms/cm)	2.4 x 10 ¹⁴	

Thermal Properties

Thermal Conductivity W/m°C	Coefficient of Thermal Expansion (cm/cm/°C)	
0.180	- 50°C to 30°C 59 x 10 ⁻⁶ 50°C to 110°C 159 x 10 ⁻⁶	

Date : March 1996
EPX Epoxy Adhesive DP460

Storage Conditions	Store product at 16 to 27°C for maximum storage life. High temperatures reduce normal storage life.	Rotate stock on a "first in-first out" basis.
Directions for Use /Clean Up	<p>Place the cartridge into the 3M EPX Applicator and clip into position.</p> <p>Remove the resealable cap.</p> <p>Expel a small quantity of adhesive and ensure both components flow freely.</p> <p>Attach correct mixer nozzle (this should have 20 or more elements).</p> <p>Dispense the adhesive as required.</p> <p>When finished either leave the nozzle in place and store, or remove the nozzle, wipe clean the tip, and replace cap.</p> <p>To re-start after storage remove the old nozzle with cured adhesive and re-fit a new nozzle, or remove the cap and fit a new nozzle.</p>	<p>Surface Preparation: The degree of surface preparation depends on the bond strength required and the environment likely to be encountered by the bonded structure. For most plastics solvent wiping with 3M VHB surface cleaner, followed by abrasion with 3M Scotchbrite 7447, followed by a further solvent wipe until clean, will give good performance (except for acetal, polyethylene and polypropylene and some other low surface energy materials). This also applies to powder coat paints and other stoved paint systems.</p> <p>The same surface preparation will also give good adhesion to metal surfaces. The objective is to remove loosely attached surface films such as oils, waxes, dusts, mill-scale, loose paints and all other</p> <p>surface contaminants in addition to enhancing mechanical adhesion. Grit-blasting using a clean, fine grit also offers excellent adhesion on many metallic substrates.</p> <p>Where humid environments are likely to be encountered by metallic substrates we recommend additional priming with 3M Scotch-Weld 3901. Alternatively, chemical conversion coating techniques combined with priming can offer the best durability.</p> <p>Clean-Up: Excess uncured adhesive can be removed with the following solvents:</p> <p>3M VHB Surface Cleaner (mild alcohol based cleaner) 3M Scotch-Grip Solvent No2. (Ketone blend) 3M Industrial Cleaner (Aerosol).</p>

Date : March 1996
EPX Epoxy Adhesive DP460

**Health & Safety
Information**

Refer to product label and Material Safety Data Sheet for health and safety information before using the product.
For information please contact your local 3M Office
www.3M.com

3M, EPX, Duo-Pak, Scotch-Grip and Scotch-Weld are trademarks of the 3M Company.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations.



3M Nederland BV

Industriële Tapes & lijmen

Postbus 193

2300 AD Leiden

e-mail:

3mbonding.nl@mmm.com

internet:

www.3m.nl/tapes

www.3m.nl/lijmen

Customer Service:

Tel.: (071)5 450 187

Fax: (071)5 450 376