

Technical Information

Technomelt Q 5432



Type of adhesive synthetic-based hotmelt

Field of application pallet securing

Product specifications

Test method

Viscosity 1.450 - 2.000 mPa.s at 160 °C

Brookfield Thermosel spindle 27

Softening point 95 - 105 °C

Ring & Ball

Product specifications Technomelt Q 5432 is suitable for securing palletized cartons, multi packs and bags made from paper or films. Due to its film properties Q 5432 allows clean palletizing and due to its low remaining tackiness an easy depalletizing.

Colour white transparent

Open time long, slightly tacky

Processing Technomelt Q 5432 is suitable for spot- as well as line- and spray application.
See also "General Instructions for the Application of Hotmelts".

Application by means of nozzle

Temperature 140 - 180 °C

Cleaning For cleaning of adhesive containers and application systems we recommend the use of our cleaning agent V 1940. During use please consider safety instructions. For the cold cleaning of surface soiling on application equipment, conveyor belts or other machine parts Melt-O-Clean can be applied. Melt-O-Clean is based on natural resources and supplies the manual cleaning also in case of strong carbonisations. Before using Melt-O-clean its suitability for lacquered synthetic coated surfaces should be tested.

Disposal see Safety Data Sheet

Security advices see Safety Data Sheet

Packaging 500 g cubes

Shelf life and

Storage conditions

In closed original packaging and under normal dry storage condition for at least 2 years without negative impact on quality.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, March 1998

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050
Email: info@van-asperen.nl www.van-asperen.nl

