

Technical Information

Adhesin CW 5748



Type of adhesive Synthetic resin solution , containing plasticizer

Field of application Tissue Converting
Core winding

Product specification

Test Method

Viscosity 7.500 \pm 2.000 mPa.s

Brookfield RVT 5/20/23
ISO 2555

pH-Value 4,5 \pm 1,0

ISO 976

Properties

Film soft-elastic

Processing

Application by means of roller and segment

Dilution The product can be diluted with cold water if required.

Cleaning Uncured adhesive residues can easily be removed with water.

Disposal see Safety Data Sheet

Protective Measures see Safety Data Sheet

Storage Conditions/ Shelf Life

In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers thoroughly after use.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, August 1999

