

Adhesin Gel 6602

Field of application: Machine made bookcase production

Description: Adhesin Gel 6602 is a protein adhesive with medium viscosity. It shows high initial tack and has good dilution properties on account of its high adhesive power.

Adhesin Gel 6602 may be thinned down depending on the quality of the book binding material. Due to its quick-tack properties it is especially suitable for use on medium-speed and high-speed bookcase machines (e.g. Hörauf , Kolbus , Stahl/VBF).

Adhesin Gel 6602 is suitable also for hot and humid countries on account of its high gelation point.

Product specification :

Viscosity: approx. 2650 mPas

Solid content: 45.7%

Refractometer value: 52%

Test Method:

60° C, Haake VT 181, 45.2 r.p.m

Properties:

Colour: light beige to light grey

Gelatinizing power: instantly, very strong ¹⁾

1) This value was determined at 22°C and 40% relative humidity. It is subject to change through changing climatic conditions and changing concentrations of the solution.

Gelation point: 39.5 °C ²⁾

2) The gelation or solidification point is defined as the temperature at which the protein adhesive gels (solidifies) under pre-defined conditions.

Open time: short

Instructions for use:

Temperature: 55 - 65 °C

The amount of adhesive per surface unit depends to a high degree on the machine type and the materials to be bonded.

**Preparation
directions:**

Adhesin Gel 6602 is molten in the heatable circulation tank at 55 - 65 °C. Please avoid temperatures above 70 °C.

When ready for use the solution should be consumed within 24 hours.

Dilution:

Addition of water (%)	0	3	6	9	12	15	18
Refracto-meter value (%)	51.8	50.3	48.7	47.1	45.6	44.0	42.5

Cleaning:

For the cold cleaning of surface soilings on application equipment, conveyor belts or other machine parts Melt-O-Clean can be applied. Melt-O-Clean is based on natural resources and supplies the manual cleaning also in case of strong carbonisations. Before using Melt-O-Clean its suitability for lacquered or synthetic coated surfaces should be tested.

Disposal:

As a rule Adhesin Gel 6602 is biodegradable or degradable in biological sewage plants. In case of doubt, contact your wastewater management authorities.

Security advices:

see Safety Data Sheet

Packaging:

Pileable 20-kg cartons containing 8 polythene wrapped portions of 2.5 kg each.

**Storage Conditions/
Shelf Life:**

Storage dry and cool. If storage conditions are observed, there will be a minimum storage life of 6 months.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Düsseldorf, April 2009

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050
Email: info@van-asperen.nl Web: www.van-asperen.nl