

Technical Information

Adhesin A 7045



Type of adhesive	Emulsion-based adhesive without plasticizer, with a low content of solvent and soaking agents.	
Field of application	Packaging Industry: Bonding of lacquered papers and cardboards. Bookbinding: Casing in of books into covers with film laminated or lacquered surfaces. Lamination of soft-PVC films and lacquered surfaces against paper and cardboard. Special Applications: Bonding of shock proof leads.	
Product specifications		Test Method
Viscosity	7.500 \pm 1.500 mPa.s	Brookfield RVT, 4/20/23, ISO 2555
pH-value	4,5 \pm 1,0	ISO 976
Product properties	Adhesin A 7045 is specially suitable to bond difficult and lacquered surfaces, alu laminated and PVDC coated papers as well as the bonding of acetate-, polystyrene-, soft-PVC and rigid-PVC films with paper and cardboard. Due to its soft elastic film properties the bonding of highly pick resistant substrates can only be judged after 24 hours.	
Film	soft elastic, very high elongation capacity	
Processing Application	by means of segment, roller, disc and nozzle Most suitable processing temperature : 18 - 25 °C.	
Dilution	Adhesin A 7045 can be diluted with cold water if required.	
Cleaning	Uncured adhesive residues can easily be removed with water. Dried adhesive films can be removed with our cleaning agent A 1920.	
Disposal	see Safety Data Sheet	
Protective Measures	see Safety Data Sheet	
Storage Conditions		
Shelf Life	In closed original packaging 9 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers carefully after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Düsseldorf, November 1999

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050
Email: info@van-asperen.nl www.van-asperen.nl

