

Technical Information

Adhesin A 7069



Type of adhesive	synthetic resin dispersion	
Field of application	Packaging industry diaphragm glueing of glasses	
Product specifications		Test method
Viscosity	6.000 + 2.000mPa.s	Brookfield RVT 4/20/23, ISO 2555
pH-value	5,0 + 1,0	ISO 976
Product properties	Adhesin A 7069 shows very good flowing properties. Adhesin A 7069 corresponds to the XIV. recommendation of the "Kunststoffkommission des BgVV".	
Film	Adhesin A 7069 forms a flexible film.	
Processing		
Application	by means of roller, segment, disc, nozzle	
Temperature	optimum working temperature: 18 - 25 ? C	
Dilution	Adhesin A 7069 can be diluted with cold water if required.	
Cleaning	Uncured and uncured adhesive residues can easily be removed with water.	
Disposal	see Safety Data Sheet	
Security advices	see Safety Data Sheet	
Shelf life	6 months in closed original packaging	
Storage conditions	optimum storage temperature: 15 - 25 ? C, protect from frost. After use close packaging thoroughly.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, July 2002