

Technical Information

Adhesin A 7088



Type of adhesive	emulsion-based adhesive without plasticizer
Field of application	Packaging Industry: Bonding of soft-PVC-films and lacquered surfaces against paper and cardboard. Good bonding properties on alu-laminated PVDC-coated surfaces as well as polystyrene films. Graphic Industry: Side glueing Casing-in of books

Product specifications	Test Method
Viscosity	5.000 \pm 1.000 mPa.s Brookfield RVT, 4/20/23, ISO 2555
pH-value	4,0 \pm 1,0 ISO 976
Product properties	Adhesin A 7088 corresponds with the recommendation XIV of the "Kunststoffkommission des BGVV".
Film	elastic with enormous elongation capacity
Application	by means of nozzles, discs, rollers Most suitable processing temperature : 18 - 25 °C.
Dilution	Adhesin A 7088 can be diluted with cold water if required.
Cleaning	Uncured adhesive residues can easily be removed with water. Dried adhesive films can be removed with our cleaning agent A 1920.
Disposal	see Safety Data Sheet
Protective Measures	see Safety Data Sheet
Storage Conditions	
Shelf Life	In closed original packaging 9 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers carefully after use.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, October 2005

