

# Technical Information

## Adhesin A 7093



<b>Type of adhesive</b>	synthetic resin dispersion, free of plasticizers	
<b>Field of application</b>	Packaging Industry Bonding of unlacquered and lacquered paper and cardboard. Lamination of rigid and soft PVC-films with absorbent materials. Diaphragm glueing. Bookbinding Casing-in of books into covers made from PVC, general bondings of PVC-materials with paper or cardboard. Billboarding Primer for billboards made of metal or aluminium	
<b>Product specifications</b>		<b>Test Method</b>
<b>Viscosity</b>	2.400 $\pm$ 500 mPa.s	Brookfield RVT 3/20/23, ISO 2555
<b>pH - value</b>	5,0 $\pm$ 1,0	ISO 976
<b>Product properties</b>	Adhesin A 7093 is a fast setting adhesive and corresponds to the recommendation XIV of BgVV	
<b>Film</b>	elastic, resistant against plasticizers, high heat resistance	
<b>Processing Application</b>	roller, segment, nozzle, disc Most suitable processing temperature: 18 - 25 °C.	
<b>Dilution</b>	Adhesin A 7093 can be diluted with cold water if required.	
<b>Cleaning</b>	Uncured adhesive residues as well as dried adhesive films can easily be removed with water. Wetting agents increase the cleaning process.	
<b>Disposal</b>	see Safety Data Sheet	
<b>Protective Measures</b>	see Safety Data Sheet	
<b>Storage Conditions/ Shelf life</b>	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers carefully after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.  
Düsseldorf, August 2002

