

Technical Information

Adhesin A 7122



Type of adhesive	synthetic resin dispersion, containing plasticizer	
Field of application	Packaging Industry: Folding box manufacturing Bonding of unlacquered and lacquered cardboards on high speed machines.	
Product specifications		Test Method
Viscosity	4.000 \pm 500 mPa.s	Brookfield RVDV, 4/20/23, ISO 2555
pH-value	4,0 \pm 1,0	ISO 976
Product properties	Adhesin A 7122 is a high concentrated, fast setting dispersion adhesive and therefore suitable for high speed folding box machines. Adhesin A 7122 conforms to § 175.105 Adhesives.	
Film	elastic	
Processing Application	By means of disc, segment and roller Most suitable processing temperature : 18 - 25 °C.	
Dilution	Adhesin A 7122 can be diluted with cold water.	
Cleaning	Uncured adhesive residues can easily be removed with water.	
Disposal	see Safety Data Sheet	
Protective Measures	see Safety Data Sheet	
Storage Conditions/Shelf Life	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers carefully after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Düsseldorf, February 2003

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050
Email: info@van-asperen.nl www.van-asperen.nl