

# Technical Information

## Adhesin A 7170



<b>Type of adhesive</b>	emulsion-based adhesive with a low content of plasticizers	
<b>Field of application</b>	Manufacture of paper- and cardboard: Lamination of papers and cardboards for unprinted and lacquered materials. Folding box manufacturing. Form sets, Mailing	
<b>Product specifications</b>		<b>Test Method</b>
<b>Viscosity</b>	100 $\pm$ 50 mPa.s	Brookfield RVDV, 1/20/23, ISO 2555
<b>pH-value</b>	5 $\pm$ 1	ISO 976
<b>Product properties</b>		
<b>Film</b>	soft elastic	
<b>Processing</b>		
<b>Application</b>	by means of electro-magnetic valves Most suitable processing temperature : 18 - 25 °C.	
<b>Dilution</b>	Adhesin A 7170 can be diluted with cold water if required.	
<b>Cleaning</b>	Uncured adhesive residues can easily be removed with water.	
<b>Disposal</b>	see Safety Data Sheet	
<b>Protective Measures</b>	see Safety Data Sheet	
<b>Storage Conditions/Shelf Life</b>	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers thoroughly after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Düsseldorf, January 2001

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad  
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050  
Email: [info@van-asperen.nl](mailto:info@van-asperen.nl) [www.van-asperen.nl](http://www.van-asperen.nl)

