

Technical Information

Adhesin A 7236



Type of adhesive	synthetic resin dispersion, containing plasticizer	
Field of application	Processing of paper and cardboard: Bonding of unprinted, printed as well as unlacquered and lacquered substrates on high speed machines.	
Product specifications		Test Method
Viscosity	900 ± 100 mPa.s	Brookfield RVDV,2/20/23, ISO 2555
pH-value	4,5 ± 1,0	ISO 976
Product properties	Adhesin A 7236 is a dispersion adhesive, which is applied by means of electric valves. Adhesin A 7236 distinguishes by a short structure (no stringing) and a clean machineability. Due to the very good reemulsifiability the drying on the nozzle could be reduced considerably.	
Film	elastic	
Processing Application	By means of an electric application equipment for spot and line gluing. Most suitable processing temperature : 18 – 25 °C.	
Dilution	Adhesin A 7236 is ready for use.	
Cleaning	Uncured adhesive residues can easily be removed with water.	
Disposal	see Safety Data Sheet	
Protective Measures	see Safety Data Sheet	
Storage Conditions/ Shelf Life	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Stir the adhesive before use. Close containers carefully after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, April 1999

