

Technical Information

Adhesin A 7237



Type of adhesive	synthetic resin dispersion, containing plasticizer
Field of application	Processing of paper and cardboard: Bonding of unprinted, printed as well as unlacquered and lacquered substrates on high speed machines. Packaging Industry: Manufacture of folding boxes

Product specifications	Test Method
Viscosity pH-value	2.000 ± 200 mPa.s $4,5 \pm 1,0$ Brookfield RVDV,3/20/23, ISO 2555 ISO 976

Product properties	Adhesin A 7237 is a dispersion adhesive, which is applied by means of electro-pneumatic valves. Adhesin A 7237 distinguishes by a short structure (no stringing) and a clean machineability. Due to the very good reemulsifiability the drying on the nozzle could be reduced considerably. Adhesin A 7237 is especially suitable for bondings where a high wet tack is required (e.g. Hesser-machines).
---------------------------	---

Film	elastic
-------------	---------

Processing Application	By means of an electro-pneumatic application equipment for line gluing; segment, roller. Most suitable processing temperature : 18 – 25 °C.
-------------------------------	---

Dilution	Adhesin A 7237 is ready for use.
-----------------	----------------------------------

Cleaning	Uncured as well as cured adhesive residues can easily be removed with water.
-----------------	--

Disposal	see Safety Data Sheet
-----------------	-----------------------

Protective Measures	see Safety Data Sheet
----------------------------	-----------------------

Storage Conditions/ Shelf Life	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Stir the adhesive before use. Close containers carefully after use.
---	---

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, April 1999

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050
Email: info@van-asperen.nl www.van-asperen.nl

