

Technical Information

Adhesin A 7259



Type of adhesive	synthetic resin based adhesive containing plasticizer	
Field of application	Mailing industrie general paper bonding; bonding of higher quality and varnished papers; lamination for cover production Envelope Industrie Window glue for envelopes. Glueing of treated OPP film on Winkler&Dünnebier machines	
Product specification		Test Method
Viscosity	1300 \pm 500 mPa.s	Brookfield RVT 3/20/23 ISO 2555
pH-value	8,5 \pm 1,5	ISO 976
Product Properties	Adhesin A 7259 is suitable for the bonding of high-quality and varnished papers as well as for lamination for cover production.	
Film	Adhesin A 7259 forms an elastic film.	
Processing Application	by means of roller, segment or disc Most suitable working temperature: 18 – 25 °C.	
Dilution	Adhesin A 7259 can be diluted with cold water if required	
Cleaning	Uncured adhesive residues as well as dried adhesive films can easily be removed with water. Wetting agents increase the cleaning process.	
Disposal	see Safety Data Sheet	
Protective Measures	see Safety Data Sheet	
Storage Conditions/ Shelf Life	In closed original packaging 3 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers thoroughly after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, December 2002

