

Technical Information

Adhesin A 7260



Type of adhesive	emulsion-based adhesive with low content of plasticizer	
Field of application	Packaging Industry: Manufacture of folding boxes Good bonding properties on lacquered and alu-laminated surfaces of papers and cardboards.	
Product specifications		Test Method
Viscosity	6.000 ± 1.000 mPa.s	Brookfield RVT, 4/20/23, ISO 2555
pH-value	4,0 ± 1,0	DIN-ISO 976
Product properties	Adhesin A 7260 is a highly concentrated, fast setting adhesive. Therefore it is quite suitable for high speed folding box machines with excellent spraying properties.	
Film	soft elastic with high elongation capacity	
Processing	Processing can be effected either by means of a bottle or a circulating pump system.	
Application	by means of segment, roller, disc Most suitable processing temperature : 18 – 25 °C.	
Dilution	Adhesin A 7260 can be diluted with cold water if required.	
Cleaning	Uncured adhesive residues can easily be removed with water. Dried adhesive films can be removed with our cleaning agent A 1920.	
Disposal	see Safety Data Sheet	
Protective Measures	see Safety Data Sheet	
Storage Conditions/ Shelf Life	In closed original packaging 9 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers carefully after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, September 1998

