

# Technical Information

## Adhesin A 7281-21



<b>Type of adhesive</b>	synthetic resin dispersion, containing plasticizer	
<b>Field of application</b>	Processing of paper and cardboard: Bonding of unprinted, printed as well as unlacquered and lacquered substrates on high speed machines.	
<b>Product specifications</b>		<b>Test Method</b>
<b>Viscosity</b>	700 ± 100 mPa.s	Brookfield RVDV,2/20/23, ISO 2555
<b>pH-value</b>	4,5 ± 1,0	ISO 976

Adhesin A 7281-21 is currently undergoing extensive practical tests and is still in the experimental stage. Technical data may change.

**Product properties** Adhesin A 7281-21 is a dispersion adhesive, which is applied by means of electric valves.  
Adhesin A 7281-21 distinguishes by a short structure (no stringing) and a clean machineability.

The adhesive corresponds to FDA 175.105.

**Film** elastic

**Processing Application** By means of an electric application equipment for spot and line gluing. Most suitable processing temperature : 18 - 25 °C.

**Dilution** Adhesin A 7281-21 is ready for use.

**Cleaning** Uncured adhesive residues can easily be removed with water.

**Disposal** see Safety Data Sheet

**Protective Measures** see Safety Data Sheet

**Storage Conditions/ Shelf Life** In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Stir the adhesive before use. Close containers thoroughly after use.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.  
Düsseldorf, April 2003

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad  
Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050  
Email: [info@van-asperen.nl](mailto:info@van-asperen.nl) Web: [www.van-asperen.nl](http://www.van-asperen.nl)

