

Technical Information

Adhesin A 7362



<u>Type of adhesive</u>	Synthetic resin dispersion, containing plasticizers	
<u>Field of application</u>	<u>Processing of paper and cardboard</u> Folding carton: Side seam gluing Bonding of dispersion- and UV-lacquered substrates as well as treated PE- and OPP-film laminated papers and cardboards. Window patching: Window patching with PS-, PE- and OPP-films, also suitable for PE-coated board. A surface treatment of at least 38 mN/m is necessary.	
<u>Product specifications</u>	<u>Test Method</u>	
Viscosity	900 \pm 150 mPa.s	Brookfield RVDV 2/20/23, ISO 2555
PH-value	8,5 \pm 1,5	ISO 976
<u>Properties</u>	Adhesin A 7362 complies with the FDA 175.105 regulation.	
Film	Slightly yellow, elastic	
<u>Processing Application</u>	By means of nozzle application system. Most suitable processing temperature : 18 – 25 °C. Avoid direct contact with copper & bronze.	
Dilution	Adhesin A 7362 is a ready to use product	
Cleaning	Uncured adhesive residues as well as dried adhesive can easily be removed with water. Wetting agent accelerate the cleaning process.	
Disposal	see Safety Data Sheet	
<u>Protective Measures</u>	see Safety Data Sheet	
<u>Storage Conditions/ Shelf Life</u>	In closed original packaging 4 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers thoroughly after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, June 2005

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320 - 260261 Fax: +31 (0) 320 – 260050 Email:
info@vanasperen.nl www.van-asperen.nl



Technologies
Industrial Adhesives