

Technical Information

Adhesin A 7371



<u>Type of adhesive</u>	Synthetic resin dispersion, containing plasticizers	
<u>Field of application</u>	Packaging Industry Bonding of lacquered (UV- and dispersion lacquers) as well as treated PE- and OPP- film laminated papers and cardboards.	
<u>Product specifications</u>		<u>Test Method</u>
<u>Viscosity</u>	7.000 \pm 1.500 mPa.s	Brookfield RVDV, 4/20/23, ISO 2555
<u>PH-value</u>	8,5 \pm 1,5	ISO 976
<u>Properties</u>	Adhesin A 7371 conforms to the FDA 175.105	
<u>Film</u>	light yellow, elastic	
<u>Processing Application</u>	By means of roller, segment and disc. Most suitable processing temperature : 18 - 25 °C. Avoid direct contact with copper & bronze .	
<u>Dilution</u>	Adhesin A 7371 can be diluted with cold water if required.	
<u>Cleaning</u>	Uncured adhesive residues can easily be removed with water. Wetting agents accelerate the cleaning process.	
<u>Disposal</u>	see Safety Data Sheet	
<u>Protective Measures</u>	see Safety Data Sheet	
<u>Storage Conditions/Shelf Life</u>	In closed original packaging 4 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost. Close containers thoroughly after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.
Düsseldorf, March 2005

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad
Tel: +31 (0) 320 - 260261 Fax: +31 (0) 320 – 260050 Email:
info@vanasperen.nl www.van-asperen.nl



Technologies
Industrial Adhesives