

Technical Information

Adhesin A 7812



Type of adhesive	synthetic resin dispersion	
Field of application	Processing of paper and cardboard Bonding of unprinted, printed as well as unlacquered and lacquered substrates on high speed machines. Bags and Pouches Bonding of longitudinal seam of unlacquered and lacquered papers.	
Product specifications		Test Method
Viscosity	850 ± 150 mPa.s	Brookfield RVT, 2/20/23, ISO 2555
pH-value	6±1	ISO 976
Product properties	Adhesin A 7812 forms an elastic film. The adhesive complies with FDA 175.105. Adhesin A 7812 distinguishes by a short structure (no stringing) and a clean machineability. Due to the very good reemulsifiability the drying on the nozzle could be reduced considerably.	
Film	elastic	
Processing		
Application	By means of an electric application equipment for spot and line glueing. Most suitable processing temperature: 18-25 °C.	
Dilution	Adhesin A 7812 is ready for use.	
Cleaning	Uncured adhesive residues can easily be removed with water	
Disposal	See Safety Data Sheet.	
Protective Measures	See Safety Data Sheet.	
Storage Conditions/ Shelf Life	In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 °C, protect from frost and do not store below 10 °C. Close containers carefully after use.	

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

