Technical Information Adhesin A 7813



Type of adhesive synthetic resin dispersion

Field of application Packaging Industry

Low viscous and fast setting adhesive for the packaging industry for lacquered and unlacquered materials. General bonding of paper.

Bags and Pouches

Bonding of longitudinal seam of unlacquered and lacquered papers.

Product specifications Test Method

Viscosity 1,700 ± 300 mPa.s Brookfield RVT, 3/20/23, ISO 2555

pH-value 6±1 ISO 976

Product properties Adhesin A 7813 forms an elastic film. The adhesive complies with FDA

175.105.

Processing

Application By means of nozzle, segment, roller or disc. Most suitable processing

temperature: 18-25 ℃.

Dilution The product can be diluted with cold water if required.

Cleaning Uncured adhesive residues can easily be removed with water

Disposal See Safety Data Sheet.

Protective Measures See Safety Data Sheet.

Storage Conditions/

Shelf Life

In closed original packaging 6 months from date of production. Optimum storage temperature: 15 - 25 $^{\circ}$ C, protect from frost and do not store below

10℃. Close containers carefully after use.

The information provided herein, especially recommendations for the usage and the application of our products, is based upon our knowledge and experience. Due to different materials used as well as to varying working conditions beyond our control we strictly recommend to carry out intensive trials to test the suitability of our products with regard to the required processes and applications. We do not accept any liability with regard to the above information or with regard to any verbal recommendation, except for cases where we are liable of gross negligence or false intention.

Van Asperen Kleefstoffen B.V. Vaartweg 106 8243 PP Lelystad Tel: +31 (0) 320-260261 Fax: +31 (0) 320-260050

Email: info@van-asperen.nl www.van-asperen.nl

A7813e.dot Page 1 Status: June.2008

