

Technomelt Q 9268 H



Hotmelt Adhesive
Almost odourless

Basis: EVA-Copolymer

Issue: 11.04.2006

Product Description

Technomelt Q 9268 H is a hotmelt adhesive, based on EVA-Copolymer which, when the recommended processing temperature is adhered to, excels in a particularly pronounced thermal stability in the hot melt. The product has a very good "hot-tack", a short setting time and is almost odourless.

Application Areas

Technomelt Q 9268 H is used for bonding of cardboards, wood and wooden materials, leather, fabric, different plastics, as well as aluminium and steel. For further applications contact our Technical Customer Service.

Technical Data

		Method
Colour:	white, nearly transparent	
Density:	approx. 1,0 g/cm ³	ASTM D 972
Solids:	100%	
Softening Point (R und B):	82 - 90°C	ASTM E 28
Viscosity (Brookfield, Spindel 27) at 160°C:	24.000 – 30.000 mPa.s	ASTM D 3236
Application temperature:	170 – 190°C	

Application

Preliminary remark

Prior to application it is necessary to read the Safety Data Sheet for information about precautionary measures and safety recommendations. Also, for chemical products exempt from compulsory labelling, the relevant precautions should always be observed.

Preparation

The substrates must be dry, free of oil, grease and dust.

Application

Technomelt Q 9268 H is using hotmelt pistols. The usual processing temperature is between 170 and 190°C. While processing, take care to maintain a gentle thermal load by keeping to the recommended working temperature, since prolonged overheating or too often repeated melting will inevitably entail quality changes in the adhesive. The stated processing temperatures are standard values which, according to the processing method, may vary within certain limits.

Apply the adhesive as closely as possible to the site where the parts to be bonded are joined and in a thickness ensuring complete and intensive coating of both surfaces. When joining materials of different adhesive properties apply the adhesive to the surface which is more difficult to join, if possible. If this is not possible, it is advisable to raise the application temperature or increase the thickness of the adhesive layer applied.

Immediately after joining, keep the parts pressed together until the bonded join is held by the adhesive itself. The time which this requires is largely dependent on the recovery of the material to be bonded and the "hot tack" of the adhesive. If the join is parted even by some tenths of millimeters during the biding stage, a ridge is formed which leads to reduced load capacity of the join.

Cleaning

For the cleaning of the application equipment we recommend to use our cleaner Terorehm-Cleaner 02.

Storage

Frost-sensitive	No
Recommended storage temp.	10°C to 20°C
Shelf-life	24 months

Packaging

Stick Ø 11,3 mm	Carton 10 Kg
-----------------	--------------

Hazard Indications/ Safety Recommendations/ Transport Regulations

see Safety Data Sheet

Important

The above data, particularly the recommendations for application and use of our products are based on our knowledge and experience. Due to the different materials and conditions of application which are beyond our knowledge and control we recommend strongly to carry out sufficient tests in order to ensure that our products are suitable for the intended processes and applications. Except for willful acts any liability based on such recommendations or any oral advice is hereby expressly excluded.

This Technical Data Sheet supersedes all previous editions.